



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08K 9/04, C09C 1/56	A1	(11) International Publication Number: WO 99/31175 (43) International Publication Date: 24 June 1999 (24.06.99)
(21) International Application Number: PCT/US98/26378 (22) International Filing Date: 11 December 1998 (11.12.98) (30) Priority Data: 08/990,715 15 December 1997 (15.12.97) US (71) Applicant: CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventors: COOKE, Joel, M.; 7 Hopkins Street, Nashua, NH 03060 (US). GALLOWAY, Collin, P.; Apartment K, 44 Bay Ridge Drive, Nashua, NH 03062 (US). BISSELL, Mark, A.; 31 Bemis Road, Pepperell, MA 01463 (US). ADAMS, Curtis, E.; 11 Lovell Road, Watertown, MA 02472 (US). YU, Michael, C.; 7 Regina Drive, Chelmsford, MA 01824 (US). BELMONT, James, A.; 8 Conant Street, Acton, MA 01720 (US). AMICI, Robert, A.; 31 Fosgate Road, Berlin, MA 01503 (US). (74) Agent: LANDO, Michelle, B.; Cabot Corporation, 157 Concord Road, P.O. Box 7001, Billerica, MA 01821-7001 (US).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: POLYMERIC PRODUCTS CONTAINING MODIFIED CARBON PRODUCTS AND METHODS OF MAKING AND USING THE SAME		
(57) Abstract Various modified carbon products are disclosed which can form a part of a polymeric product containing the modified carbon product and a polymer. One type of modified carbon product disclosed is a carbon product having attached at least one organic group, monomeric group, or polymeric group. Another type of modified carbon product disclosed is a carbon product having attached a group having the formula: $-Ar-CO_2-R$ or $-C_nH_{2n}CO_2-R$, where R is an organic group, monomeric group, or a polymeric group. The third type of modified carbon product contains a) a carbon product having attached at least one organic group directly attached to the carbon product, b) at least one ionic group, ionizable group, or a mixture thereof attached to the organic group, and c) at least one counter-ionic group or counter-ionizable group with at least one organic group, monomeric group, or polymeric group, or mixture thereof, where the counter-ionic or counter-ionizable group is attached to the ionic and/or ionizable group. A method of improving the dispersion of carbon products in polymers is also disclosed which involves dispersing the modified carbon products described above in a polymer to form a polymeric product.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**POLYMERIC PRODUCTS CONTAINING MODIFIED CARBON
PRODUCTS AND METHODS OF MAKING AND USING THE SAME**

5 BACKGROUND OF THE INVENTION

The present invention relates to polymers and more particularly relates to the use of fillers, colorants, UV stabilizers, or reinforcement agents in polymers.

Generally, many articles formed from polymers, such as plastics, contain reinforcement agents, fillers, and/or colorants. Generally, such agents, fillers, and colorants like carbon black, are
10 incorporated into the polymers with the use of masterbatches. The masterbatches are used because the direct addition of reinforcement agents, fillers, and colorants like carbon black, may not adequately disperse amongst the polymer which would then result in a less than desirable polymer product. Masterbatches are used as a means to incorporate the reinforcement agent, filler, or colorant, like carbon black, into a polymer. These conventional masterbatches therefore serve as an
15 intermediate step to the ultimate introduction of reinforcement agents, fillers, and colorants into a polymer.

It would be desirable to polymer manufacturers if agents like carbon black could be directly incorporated into the polymer at the same time that the polymers are being formed or at the time when polymers are being formed into a desired article; thus avoiding the need for conventional
20 masterbatches.

SUMMARY OF THE INVENTION

A feature of the present invention is to provide UV stabilizers, reinforcement agents, fillers, and/or colorants like carbon products, such as carbon black, which can be directly incorporated into polymers.

25 Another feature of the present invention is to provide carbon products which are capable of being dispersed in polymer products to a better degree than conventional carbon products like carbon black.

An additional feature of the present invention is to provide masterbatches which contain higher levels of carbon product, like carbon black, than conventional masterbatches.

Additional features and advantages of the present invention will be set forth in part in the description which follows, and in part will be apparent from the description, or may be learned by practice of the present invention.

To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described herein, the present invention relates to a polymer product comprising a polymer and a modified carbon product dispersed therein. The modified carbon product comprises a carbon product having attached at least one organic group, monomeric group and/or polymeric group.

The present invention further relates to a polymeric product comprising a polymer and a modified carbon product dispersed therein, wherein the modified carbon product comprises a carbon product having attached at least one group having the formula: $-Ar-CO_2-R$ or $C_nH_{2n}CO_2-R$, where R is an organic group, a monomeric group, or a polymeric group, and n is preferably an integer of from 1 to 12.

In addition, the present invention relates to a modified carbon product comprising a) a carbon product having attached at least one organic group directly attached to the carbon product, b) at least one ionic group, ionizable group, or a mixture thereof attached to said organic group, and c) at least one counter-ionic group with at least one organic group, monomeric group, or polymeric group, or counter-ionizable group with at least one organic group, monomeric group, or polymeric group, or a mixture thereof, wherein the counter-ionic or counter-ionizable group is attached to the ionic and/or ionizable group.

The present invention also relates to polymeric products containing a polymer and one or more of the modified carbon products described immediately above.

The present invention also relates to the modified carbon products used above in the polymeric products.

The present invention further relates to a method of improving the dispersion of carbon products in polymeric products using one or more of the modified carbon products of the present invention.

Also, the present invention relates to masterbatches comprising one or more polymers and one or more modified carbon products of the present invention.

It is to be understood that both the forgoing general description and the following detailed description are exemplary and explanatory only and are intended to provide further explanation of the present invention, as claimed.

DETAILED DESCRIPTION OF THE PRESENT INVENTION

In general, the present invention relates to the use of modified carbon products in polymers. Thus, the present invention relates to a polymeric product containing at least one polymer and at least one modified carbon product dispersed in the polymer and compatible with the polymer.

For purposes of the present invention, one or more polymers can be present in the polymeric product of the present invention. The polymer can be a thermoplastic polymer or a thermosetting polymer. Further, the polymer can be a homopolymer, copolymer, terpolymer, and/or a polymer containing any number of different repeating units. Further, the polymer present in the polymeric product of the present invention can be any type of polymer, such as a random polymer, alternating polymer, graft polymer, block polymer, star-like polymer, and/or comb-like polymer. The polymer used in the polymeric product of the present invention can also be one or more polyblends. The polymer can be an interpenetrating polymer network (IPN); simultaneous interpenetrating polymer network (SIN); or interpenetrating elastomeric network (IEN).

Specific examples of polymers include, but are not limited to, linear-high polymers such as polyethylene, poly(vinylchloride), polyisobutylene, polystyrene, polycaprolactam (nylon), polyisoprene, and the like. Other general classes of polymers which can represent the polymers present in the polymeric product of the present invention are polyamides, polycarbonates, polyelectrolytes, polyesters, polyethers, (polyhydroxy)benzenes, polyimides, polymers containing sulfur (such as polysulfides, (polyphenylene) sulfide, and polysulfones), polyolefins, polymethylbenzenes, polystyrene and styrene copolymers (ABS included), acetal polymers, acrylic polymers, acrylonitrile polymers and copolymers, polyolefins containing halogen (such as polyvinyl chloride and polyvinylidene chloride), fluoropolymers, ionomeric polymers, polymers containing

ketone group(s), liquid crystal polymers, polyamide-imides, polymers containing olefinic double bond(s) (such as polybutadiene, polydicyclopentadiene), polyolefin copolymers, polyphenylene oxides, polyurethanes, thermoplastic elastomers and the like.

Preferably, the polymer present in the polymeric product of the present invention is a
5 polyolefin or polyethylene, more preferably, polymers of alpha olefins derived from ethylene, 1-butene, propylene, 1-hexene, 1-octene, 4-methyl-1-pentene and substituted alpha-olefins and the like, copolymers of: ethylene, 1-butene, propylene, 1-hexene, 1-octene, 4-methyl-1-pentene and substituted alpha-olefins and the like, and terpolymers comprised primarily of ethylene, 1-butene, propylene, 1-hexene, 1-octene, 4-methyl-1-pentene and substituted alpha-olefins and the like.

10 Generally, the polymers described in Volume 18 of the Encyclopedia of Chemical Technology, KIRK-OTHMER, (1982), page 328 to page 887, and Modern Plastics Encyclopedia '98, pages B-3 to B-210, both incorporated in their entirety herein by reference, can be used as the polymer in the polymeric product of the present invention.

The polymer used in the polymeric product of the present invention can be prepared in a
15 number of ways and such ways are known to those skilled in the art. The above referenced KIRK-OTHMER section and Modern Plastics Encyclopedia provide methods in which these polymers can be prepared.

With respect to the modified carbon product also present in the polymeric product, there are generally three classes of modified carbon products which will be described below.

20 For purposes of the present invention, a carbon product can be a carbon capable of reacting with a diazonium salt to form the above-mentioned modified carbon products. The carbon may be of the crystalline or amorphous type. Examples include, but are not limited to, graphite, carbon black, vitreous carbon, activated charcoal, carbon fibers and activated carbon. Finely divided forms of the above are preferred; also, it is also possible to utilize mixtures of different carbons.

25 Also, for purposes of the present invention, carbon product includes an aggregate comprising a carbon phase and a silicon-containing species phase. A description of this aggregate as well as means of making this aggregate are described in PCT Publication No. WO 96/37547 as well as U.S. Patent Application Nos. 08/446,141; 08/446,142; 08/528,895; and 08/750,017. All of these

patents, publications, and patent applications are hereby incorporated in their entireties herein by reference.

The carbon product, for purposes of the present invention, can also be an aggregate comprising a carbon phase and metal-containing species phase where the metal-containing species
5 phase can be a variety of different metals such as magnesium, calcium, titanium, vanadium, cobalt, nickel, zirconium, tin, antimony, chromium, neodymium, lead, tellurium, barium, cesium, iron, molybdenum, aluminum, and zinc, and mixtures thereof. The aggregate comprising the carbon phase and a metal-containing species phase is described in U.S. Patent Application No. 08/828,785 filed March 27, 1997, also hereby incorporated in its entirety herein by reference.

10 Also, for purposes of the present invention, a carbon product includes a silica-coated carbon black, such as that described in PCT Publication No. WO 96/37547, published November 28, 1996, also incorporated in its entirety herein by reference.

The first type of modified carbon product is a modified carbon product containing a carbon product having attached at least one organic group, monomeric group, or polymeric group. The
15 organic group can be an aromatic group or an alkyl group.

The polymeric group can be any polymeric group capable of being attached to a carbon product. The polymeric group can be a polyolefin group, a polystyrenic group, a polyacrylate group, a polyamide group, a polyester group, or mixtures thereof. Monomeric groups are monomeric versions of the polymeric groups.

20 The organic group can also be an olefin group, a styrenic group, an acrylate group, an amide group, an ester, or mixtures thereof. The organic group can also be an aromatic group or an alkyl group, either group with an olefin group, a styrenic group, an acrylate group, an amide group, an ester group, or mixtures thereof, wherein preferably the aromatic group, or the alkyl group, like a C_1 - C_{12} group, is directly attached to the carbon product.

25 The polymeric group can include an aromatic group or an alkyl group, like a C_1 - C_{12} group, either group with a polyolefin group, a polystyrenic group, a polyacrylate group, a polyamide group, an polyester group, or mixtures thereof.

The organic group can also comprise an aralkyl group or alkylaryl group, which is preferably directly attached to the carbon product. Other examples of organic groups include a C_{13} - C_{100} alkyl group, and more preferably a C_{30} - C_{60} alkyl group.

More preferred examples of the organic group are organic groups having the following formulas (hyphens on one or more ends represents an attachment to a carbon product or to another group):

- Ar-CO₂(C_mH_{2m+1}), where m = 0 to about 20;
 - Ar-(C_nH_{2n+1}), where n = 1 to about 50;
 - Ar-C_pH_{2p} Ar-, where p = 1 to about 10;
 - Ar-CX₃, where X is a halogen atom;
 - Ar-O-CX₃, where X is a halogen atom;
 - Ar-SO₃;
 - Ar-SO₂(C_qH_{2q+1}), where q = about 2 to about 10;
 - Ar-S₂-Ar-NH₂;
 - Ar-S₂-Ar-;
 - ArSO₂H;
- or mixtures thereof.

Preferred mixtures of organic groups include the following:

- Ar-SO₃ and -Ar(C_nH_{2n+1}), where n = 1 to about 50;
- Ar-S₂-Ar-NH₂ and -ArC_pH_{2p}Ar-, where p = 1 to about 10;
- Ar-S₂-Ar- and -ArC_pH_{2p}Ar-, where p = 1 to about 10; or
- at least two different -Ar-CO₂(C_mH_{2m+1}), where m = 0 to about 20.

The various organic, monomeric, and polymeric groups described above and below which are part of the modified carbon product can be unsubstituted or substituted and can be branched or linear.

One process for attaching an organic group to the carbon product involves the reaction of at least one diazonium salt with a carbon product in the absence of an externally applied current sufficient to reduce the diazonium salt. That is, the reaction between the diazonium salt and the

carbon product proceeds without an external source of electrons sufficient to reduce the diazonium salt. Mixtures of different diazonium salts may be used in the process of the invention. This process can be carried out under a variety of reaction conditions and in any type of reaction medium, including both protic and aprotic solvent systems or slurries.

5 In another process, at least one diazonium salt reacts with a carbon product in a protic reaction medium. Mixtures of different diazonium salts may be used in this process of the invention. This process can also be carried out under a variety of reaction conditions.

In both processes, the diazonium salt can be formed *in situ*. If desired, in either process, the carbon product can be isolated and dried by means known in the art. Furthermore, the resultant
10 carbon product can be treated to remove impurities by known techniques. Various specific embodiments of these processes are discussed below.

These processes can be carried out under a wide variety of conditions and in general are not limited by any particular condition. The reaction conditions must be such that the particular diazonium salt is sufficiently stable to allow it to react with the carbon product. Thus, the processes
15 can be carried out under reaction conditions where the diazonium salt is short lived. The reaction between the diazonium salt and the carbon product occurs, for example, over a wide range of pH and temperature. The processes can be carried out at acidic, neutral, and basic pH. Preferably, the pH ranges from about 1 to 9. The reaction temperature may range from 0°C to 100°C.

Diazonium salts, as known in the art, may be formed for example by the reaction of primary
20 amines with aqueous solutions of nitrous acid. A general discussion of diazonium salts and methods for their preparation is found in Morrison and Boyd, Organic Chemistry, 5th Ed., pp. 973-983, (Allyn and Bacon, Inc. 1987) and March, Advanced Organic Chemistry: Reactions, Mechanisms, and Structures, 4th Ed., (Wiley, 1992). According to this invention, a diazonium salt is an organic compound having one or more diazonium groups.

25 The diazonium salt may be prepared prior to reaction with the carbon product or generated *in situ* using techniques known in the art. *In situ* generation also allows the use of unstable diazonium salts such as alkyl diazonium salts and avoids unnecessary handling or manipulation of the diazonium salt. Both the nitrous acid and the diazonium salt can be generated *in situ*.

A diazonium salt, as is known in the art, may be generated by reacting a primary amine, a nitrite and an acid. The nitrite may be any metal nitrite, such as lithium nitrite, sodium nitrite, potassium nitrite, or zinc nitrite, or any organic nitrite such as for example isoamyl nitrite or ethyl nitrite. The acid may be any acid, inorganic or organic, which is effective in the generation of the diazonium salt. Acids include nitric acid, HNO_3 , hydrochloric acid, HCl , and sulfuric acid, H_2SO_4 .

The diazonium salt may also be generated by reacting the primary amine with an aqueous solution of nitrogen dioxide. The aqueous solution of nitrogen dioxide, $\text{NO}_2/\text{H}_2\text{O}$, provides the nitrous acid needed to generate the diazonium salt.

Generating the diazonium salt in the presence of excess HCl may be less preferred than other alternatives because HCl is corrosive to stainless steel. Generation of the diazonium salt with $\text{NO}_2/\text{H}_2\text{O}$ has the additional advantage of being less corrosive to stainless steel or other metals commonly used for reaction vessels. Generation using $\text{H}_2\text{SO}_4/\text{NaNO}_2$ or $\text{HNO}_3/\text{NaNO}_2$ are also relatively non-corrosive.

In general, generating a diazonium salt from a primary amine, a nitrite, and an acid requires two equivalents of acid based on the amount of amine used. In an *in situ* process, the diazonium salt can be generated using one equivalent of the acid. When the primary amine contains a strong acid group, adding a separate acid may not be necessary. The acid group or groups of the primary amine can supply one or both of the needed equivalents of acid. When the primary amine contains a strong acid group, preferably either no additional acid or up to one equivalent of additional acid is added to a process of the invention to generate the diazonium salt *in situ*. A slight excess of additional acid may be used. One example of such a primary amine is para-aminobenzenesulfonic acid (sulfanilic acid).

In general, diazonium salts are thermally unstable. They are typically prepared in solution at low temperatures, such as $0-5^\circ\text{C}$, and used without isolation of the salt. Heating solutions of some diazonium salts may liberate nitrogen and form either the corresponding alcohols in acidic media or the organic free radicals in basic media.

However, the diazonium salt need only be sufficiently stable to allow reaction with the carbon product. Thus, the processes can be carried out with some diazonium salts otherwise considered to be unstable and subject to decomposition. Some decomposition processes may compete with the reaction between the carbon product and the diazonium salt and may reduce the total number of organic groups attached to the carbon product. Further, the reaction may be carried out at elevated temperatures where many diazonium salts may be susceptible to decomposition. Elevated temperatures may also advantageously increase the solubility of the diazonium salt in the reaction medium and improve its handling during the process. However, elevated temperatures may result in some loss of the diazonium salt due to other decomposition processes.

Reagents can be added to form the diazonium salt *in situ*, to a suspension of carbon product in the reaction medium, *for example*, water. Thus, a carbon product suspension to be used may already contain one or more reagents to generate the diazonium salt and the process accomplished by adding the remaining reagents.

Reactions to form a diazonium salt are compatible with a large variety of functional groups commonly found on organic compounds. Thus, only the availability of a diazonium salt for reaction with a carbon product limits the processes of the invention.

The processes can be carried out in any reaction medium which allows the reaction between the diazonium salt and the carbon product to proceed. The reaction medium can be a solvent-based system. The solvent may be a protic solvent, an aprotic solvent, or a mixture of solvents. Protic solvents are solvents, like water or methanol, containing a hydrogen attached to an oxygen or nitrogen and thus are sufficiently acidic to form hydrogen bonds. Aprotic solvents are solvents which do not contain an acidic hydrogen as defined above. Aprotic solvents include, for example, solvents such as hexanes, tetrahydrofuran (THF), acetonitrile, and benzonitrile. For a discussion of protic and aprotic solvents see Morrison and Boyd, Organic Chemistry, 5th Ed., pp. 228-231, (Allyn and Bacon, Inc. 1987).

The processes can be carried out in a protic reaction medium, that is, in a protic solvent alone or a mixture of solvents which contains at least one protic solvent. Preferred protic media include, but are not limited to water, aqueous media containing water and other solvents, alcohols,

and any media containing an alcohol, or mixtures of such media.

The reaction between a diazonium salt and a carbon product can take place with any type of carbon product, for example, in fluffy or pelleted form. In one embodiment designed to reduce production costs, the reaction occurs during a process for forming carbon product pellets. For example, a carbon black product of the invention can be prepared in a dry drum by spraying a solution or slurry of a diazonium salt onto a carbon black. Alternatively, the carbon product can be prepared by pelletizing a carbon product in the presence of a solvent system, such as water, containing the diazonium salt or the reagents to generate the diazonium salt *in situ*. Aqueous solvent systems are preferred. Accordingly, another embodiment provides a process for forming a pelletized carbon product comprising the steps of: introducing a carbon product and an aqueous slurry or solution of a diazonium salt into a pelletizer, reacting the diazonium salt with the carbon product to attach an organic group to the carbon product, and pelletizing the resulting carbon product having an attached organic group. The pelletized carbon product may then be dried using conventional techniques.

In general, the processes produce inorganic by-products, such as salts. In some end uses, such as those discussed below, these by-products may be undesirable. Several possible ways to produce a modified carbon product without unwanted inorganic by-products or salts are as follows:

First, the diazonium salt can be purified before use by removing the unwanted inorganic by-product using means known in the art. Second, the diazonium salt can be generated with the use of an organic nitrite as the diazotization agent yielding the corresponding alcohol rather than an inorganic salt. Third, when the diazonium salt is generated from an amine having an acid group and aqueous NO_2 , no inorganic salts are formed. Other ways may be known to those of skill in the art.

In addition to the inorganic by-products, a process may also produce organic by-products. They can be removed, for example, by extraction with organic solvents. Other ways of obtaining products without unwanted organic by-products may be known to those of skill in the art and include washing or removal of ions by reverse osmosis.

The reaction between a diazonium salt and a carbon product forms a modified carbon product having an organic group attached to the carbon product. The diazonium salt may contain the

organic group to be attached to the carbon product. It may be possible to produce the modified carbon products used in this invention by other means known to those skilled in the art.

The organic group may be an aliphatic group, a cyclic organic group, or an organic compound having an aliphatic portion and a cyclic portion. As discussed above, the diazonium salt employed in the processes can be derived from a primary amine having one of these groups and being capable of forming, even transiently, a diazonium salt. The organic group may be substituted or unsubstituted, branched or unbranched. Aliphatic groups include, for example, groups derived from alkanes, alkenes, alcohols, ethers, aldehydes, ketones, carboxylic acids, and carbohydrates. Cyclic organic groups include, but are not limited to, alicyclic hydrocarbon groups (*for example*, cycloalkyls, cycloalkenyls), heterocyclic hydrocarbon groups (*for example*, pyrrolidinyl, pyrrolinyl, piperidinyl, morpholinyl, and the like), aryl groups (*for example*, phenyl, naphthyl, anthracenyl, and the like), and heteroaryl groups (imidazolyl, pyrazolyl, pyridinyl, thienyl, thiazolyl, furyl, indolyl, and the like). As the steric hinderance of a substituted organic group increases, the number of organic groups attached to the carbon product from the reaction between the diazonium salt and the carbon product may be diminished.

When the organic group is substituted, it may contain any functional group compatible with the formation of a diazonium salt. Functional groups include, but are not limited to, R, OR, COR, COOR, OCOR, carboxylate salts such as COOLi, COONa, COOK, COO⁻NR₄⁺, halogen, CN, NR₂, SO₃H, sulfonate salts such as SO₃Li, SO₃Na, SO₃K, SO₃⁻NR₄⁺, OSO₃H, OSO₃⁻ salts, NR(COR), CONR₂, NO₂, PO₃H₂, phosphonate salts such as PO₃HNa and PO₃Na₂, phosphate salts such as OPO₃HNa and OPO₃Na₂, N=NR, NR₃⁺X⁻, PR₃⁺X⁻, S₂R, SSO₃H, SSO₃⁻ salts, SO₂NRR', SO₂SR, SNRR', SNQ, SO₂NQ, CO₂NQ, S-(1,4-piperazinediyl)-SR, 2-(1,3-dithianyl) 2-(1,3-dithiolanyl), SOR, and SO₂R. R and R', which can be the same or different, are independently hydrogen, branched or unbranched C₁-C₂₀ substituted or unsubstituted, saturated or unsaturated hydrocarbon, e.g., alkyl, alkenyl, alkynyl, substituted or unsubstituted aryl, substituted or unsubstituted heteroaryl, substituted or unsubstituted alkylaryl, or substituted or unsubstituted arylalkyl. The integer k ranges from 1-8 and preferably from 2-4. The anion X⁻ is a halide or an anion derived from a mineral or organic acid. Q is (CH₂)_n, (CH₂)_nO(CH₂)_n, (CH₂)_nNR(CH₂)_n, or (CH₂)_nS(CH₂)_n, where

w is an integer from 2 to 6 and x and z are integers from 1 to 6.

The organic group can be an aromatic group of the formula $A_y\text{Ar}$ -, which corresponds to a primary amine of the formula $A_y\text{ArNH}_2$. In this formula, the variables have the following meanings:

Ar is an aromatic radical such as an aryl or heteroaryl group. Preferably, Ar is selected from the group consisting of phenyl, naphthyl, anthracenyl, phenanthrenyl, biphenyl, pyridinyl, benzothiadiazolyl, and benzothiazolyl; A is a substituent on the aromatic radical independently selected from a preferred functional group described above or A is a linear, branched or cyclic hydrocarbon radical (preferably containing 1 to 20 carbon atoms), unsubstituted or substituted with one or more of those functional groups; and y is an integer from 1 to the total number of -CH radicals in the aromatic radical. For instance, y is an integer from 1 to 5 when Ar is phenyl, 1 to 7 when Ar is naphthyl, 1 to 9 when Ar is anthracenyl, phenanthrenyl, or biphenyl, or 1 to 4 when Ar is pyridinyl. In the above formula, specific examples of R and R' are $\text{NH}_2\text{-C}_6\text{H}_4\text{-}$, $\text{CH}_2\text{CH}_2\text{-C}_6\text{H}_4\text{-NH}_2$, $\text{CH}_2\text{-C}_6\text{H}_4\text{-NH}_2$, and C_6H_5 .

Another set of organic groups which may be attached to the carbon product are organic groups substituted with an ionic or an ionizable group as a functional group. An ionizable group is one which is capable of forming an ionic group in the medium of use. The ionic group may be an anionic group or a cationic group and the ionizable group may form an anion or a cation.

Ionizable functional groups forming anions include, for example, acidic groups or salts of acidic groups. The organic groups, therefore, include groups derived from organic acids. When the organic group contains an ionizable group forming an anion, such an organic group can have a) an aromatic group and b) at least one acidic group having a pKa of less than 11, or at least one salt of an acidic group having a pKa of less than 11, or a mixture of at least one acidic group having a pKa of less than 11 and at least one salt of an acidic group having a pKa of less than 11. The pKa of the acidic group refers to the pKa of the organic group as a whole, not just the acidic substituent. More preferably, the pKa is less than 10 and most preferably less than 9. The aromatic group of the organic group can be directly attached to the carbon product. The aromatic group may be further substituted or unsubstituted, for example, with alkyl groups. The organic group can be a phenyl or a naphthyl group and the acidic group is a sulfonic acid group, a sulfinic acid group, a phosphonic acid

group, or a carboxylic acid group. Examples of these acidic groups and their salts are discussed above. The organic group can be a substituted or unsubstituted sulfophenyl group or a salt thereof; a substituted or unsubstituted (polysulfo)phenyl group or a salt thereof; a substituted or unsubstituted sulfonaphthyl group or a salt thereof; or a substituted or unsubstituted (polysulfo)naphthyl group or a salt thereof. An example of a substituted sulfophenyl group is hydroxysulfophenyl group or a salt thereof.

Specific organic groups having an ionizable functional group forming an anion (and their corresponding primary amines) are p-sulfophenyl (p-sulfanilic acid), 4-hydroxy-3-sulfophenyl (2-hydroxy-5-amino-benzenesulfonic acid), and 2-sulfoethyl (2-aminoethanesulfonic acid). Other organic groups having ionizable functional groups forming anions can also be used.

Amines represent examples of ionizable functional groups that form cationic groups. For example, amines may be protonated to form ammonium groups in acidic media. An organic group having an amine substituent can have a pK_b of less than 5. Quaternary ammonium groups ($-NR_3^+$) and quaternary phosphonium groups ($-PR_3^+$) also represent examples of cationic groups. The organic group can contain an aromatic group such as a phenyl or a naphthyl group and a quaternary ammonium or a quaternary phosphonium group. The aromatic group can be directly attached to the carbon product. Quaternized cyclic amines, and even quaternized aromatic amines, can also be used as the organic group. Thus, N-substituted pyridinium compounds, such as N-methyl-pyridyl, can be used in this regard. Examples of organic groups include, but are not limited to, $(C_3H_7N)C_2H_5^+$, $C_6H_4(NC_3H_7)^+$, $C_6H_4COCH_2N(CH_3)_3^+$, $C_6H_4COCH_2(NC_3H_7)^+$, $(C_3H_7N)CH_3^+$, and $C_6H_4CH_2N(CH_3)_3^+$.

An advantage of the modified carbon products having an attached organic group substituted with an ionic or an ionizable group is that the modified carbon product may have increased water dispersibility relative to the corresponding untreated carbon product. Water dispersibility of a modified carbon product increases with the number of organic groups attached to the carbon black having an ionizable group or the number of ionizable groups attached to a given organic group. Thus, increasing the number of ionizable groups associated with the modified carbon product should increase its water dispersibility and permits control of the water dispersibility to a desired level. It

can be noted that the water dispersibility of a modified carbon product containing an amine as the organic group attached to the carbon product may be increased by acidifying the aqueous medium.

Because the water dispersibility of the modified carbon products depends to some extent on charge stabilization, the ionic strength of the aqueous medium can be less than 0.1 molar. The ionic strength can also be less than 0.01 molar.

When such a water dispersible modified carbon product is prepared, the ionic or ionizable groups can be ionized in the reaction medium. The resulting product solution or slurry may be used as is or diluted prior to use. Alternatively, the modified carbon product may be dried by techniques used for conventional carbon blacks. These techniques include, but are not limited to, drying in ovens and rotary kilns. Overdrying, however, may cause a loss in the degree of water dispersibility.

In addition to their water dispersibility, modified carbon products having an organic group substituted with an ionic or an ionizable group may also be dispersible in polar organic solvents such as dimethylsulfoxide (DMSO), and formamide. In alcohols such as methanol or ethanol, use of complexing agents such as crown ethers increases the dispersibility of carbon black products having an organic group containing a metal salt of an acidic group.

Aromatic sulfides encompass another group of organic groups. Modified carbon products having aromatic sulfide groups are particularly useful in rubber compositions. These aromatic sulfides can be represented by the formulas $\text{Ar}(\text{CH}_2)_k\text{S}_q(\text{CH}_2)_r\text{Ar}'$ or $\text{A}-(\text{CH}_2)_q\text{S}_k(\text{CH}_2)_r\text{Ar}''$ wherein Ar and Ar' are independently substituted or unsubstituted arylene or heteroarylene groups, Ar'' is an aryl or heteroaryl group, k is 1 to 8 and q and r are 0-4. Substituted aryl groups would include substituted alkylaryl groups. Arylene groups can include phenylene groups, particularly p-phenylene groups, or benzothiazolylene groups. Aryl groups can include phenyl, naphthyl and benzothiazolyl.

The number of sulfurs present, defined by k preferably ranges from 2 to 4. Modified carbon products can have an attached aromatic sulfide organic group of the formula $-(\text{C}_6\text{H}_4)_k-\text{S}_q-(\text{C}_6\text{H}_4)_r-$, where k is an integer from 1 to 8, and more preferably where k ranges from 2 to 4. Aromatic sulfide groups can be bis-para- $(\text{C}_6\text{H}_4)_k-\text{S}_q-(\text{C}_6\text{H}_4)_r-$ and para- $(\text{C}_6\text{H}_4)_k-\text{S}_q-(\text{C}_6\text{H}_4)_r$. The diazonium salts of these aromatic sulfide groups may be conveniently prepared from their corresponding primary amines, $\text{H}_2\text{N}-\text{Ar}-\text{S}_q-\text{Ar}'-\text{NH}_2$ or $\text{H}_2\text{N}-\text{Ar}-\text{S}_q-\text{Ar}''$. Groups include dithiodi-4,1-phenylene, tetrathiodi-4,1-

- phenylene, phenyldithiophenylene, dithiodi-4,1-(3-chlorophenylene), $-(4-C_6H_4)-S-S-(2-C_6H_4NS)$, $-(4-C_6H_4)-S-S-(4-C_6H_4)-OH$, $-6-(2-C_6H_4NS)-SH$, $-(4-C_6H_4)-CH_2CH_2-S-S-CH_2CH_2-(4-C_6H_4)-$, $-(4-C_6H_4)-CH_2CH_2-S-S-S-CH_2CH_2-(4-C_6H_4)-$, $-(2-C_6H_4)-S-S-(2-C_6H_4)-$, $-(3-C_6H_4)-S-S-(3-C_6H_4)-$, $-6-(C_6H_5N_2S)$, $-6-(2-C_6H_4NS)-S-NRR'$ where RR' is $-CH_2CH_2OCH_2CH_2-$, $-(4-C_6H_4)-S-S-S-(4-C_6H_4)-$, $-(4-C_6H_4)-CH=CH_2$, $-(4-C_6H_4)-S-SO_3H$, $-(4-C_6H_4)-SO_2NH-(4-C_6H_4)-S-S-(4-C_6H_4)-NHSO_2-(4-C_6H_4)-$, $-6-(2-C_6H_4NS)-S-S-2-(6-C_6H_4NS)-$, $-(4-C_6H_4)-S-CH_2-(4-C_6H_4)-$, $-(4-C_6H_4)-SO_2-S-(4-C_6H_4)-$, $-(4-C_6H_4)-CH_2-S-CH_2-(4-C_6H_4)-$, $-(3-C_6H_4)-CH_2-S-CH_2-(3-C_6H_4)-$, $-(4-C_6H_4)-CH_2-S-S-CH_2-(4-C_6H_4)-$, $-(3-C_6H_4)-CH_2-S-S-CH_2-(3-C_6H_4)-$, $-(4-C_6H_4)-S-NRR'$ where RR' is $-CH_2CH_2OCH_2CH_2-$, $-(4-C_6H_4)-SO_2NH-CH_2CH_2-S-S-CH_2CH_2-NHSO_2-(4-C_6H_4)-$, $-(4-C_6H_4)-2-(1,3-dithianyl)-$, and $-(4-C_6H_4)-S-(1,4-$
- 5
- 10 piperizinediyl)-S-(4-C₆H₄)-.

Another set of organic groups which may be attached to the carbon product are organic groups having an aminophenyl, such as $(C_6H_4)-NH_2$, $(C_6H_4)-CH_2-(C_6H_4)-NH_2$, $(C_6H_4)-SO_2-(C_6H_4)-NH_2$. Organic groups also include aromatic sulfides, represented by the formulas $Ar-S_n-Ar'$ or $Ar-S_n-Ar''$, wherein Ar and Ar' are independently arylene groups, Ar'' is an aryl and n is 1 to 8. Methods


15 for attaching such organic groups to carbon product are discussed in U.S. patent applications serial nos. 08/356,660, 08/572,525, and 08/356,459, the disclosures of which are fully incorporated by reference herein.

The second type of modified carbon product which can be part of the polymeric product along with a polymer is a carbon product having attached a group having the formula: $-Ar-CO_2-R$,

20 where R is an organic group, monomeric group, or a polymeric group. The organic groups, monomeric groups, and polymeric groups described above with respect to the first type of modified carbon products can be the same with respect to this embodiment as well. Another formula is $-C_nH_{2n}-CO_2-R$, where n is preferably an integer of from 1 to 12. Specific examples of R groups are $C_{20}-C_{30}$ alkyl groups.

25 These modified carbon products can be prepared using a carbon product that is first functionalized with a diazonium salt, like the diazonium salt of 4-aminobenzoic acid. For this initial treatment, an equivalent of acid is used so that the treatment yields attached carboxylic acid groups. The acid groups are then esterified with an R containing group, for instance, long chain aliphatic

alcohols, using p-toluenesulfonic acid as the catalyst, as shown below, where R in this formula is at least one organic, monomeric, or polymeric group.



Carboxylated Carbon Product

A third type of modified carbon product is a carbon product having attached a) at least one organic group directly attached to the carbon product, b) at least one ionic group, ionizable group, or mixture thereof attached to the organic group, and c) at least counter-ionic group with at least one organic group, monomeric group, or polymeric group, a counter-ionizable group with at least one organic group, monomeric group, or polymeric group, or a mixture thereof, wherein the counter-ionic group, or counter-ionizable group is attached to the ionic group and/or ionizable group.

10

The organic group and polymeric group mentioned in the above embodiments can be the same for this embodiment. The monomeric group would simply be monomeric versions of the polymeric groups described above. For instance, examples of monomeric groups include, but are not limited to, an olefin group, a styrenic group, an acrylate group, an amide group, an ester group, or mixtures thereof.

15

Examples of the ionic group or ionizable group are the same as described above. The ionic group or ionizable group can be an anionic group or a cationic group. Preferred examples of the counter-ionic group or counter-ionizable group include nitrogen-based groups and phosphorous based groups.

20


Other examples of organic groups include a $\text{C}_1\text{-C}_{30}$ alkyl group, more preferably a $\text{C}_1\text{-C}_{20}$ alkyl group. Other examples of organic groups include an oleyl group, a linoleyl group, a linolenyl group or mixtures thereof. Other examples of organic groups include a 2-ditetradecylglutarate group or a hexa-decyl group.

25

These modified carbon products can be prepared using a carbon product that is first functionalized with at least one functional group, such as sodium sulfonate groups, for instance using

the diazonium salt of sulfanilic acid as described earlier. This process results in the chemical deagglomeration of the carbon product. The degree of deagglomeration can be measured at this stage by particle size analysis and 325 mesh residue.

Next, an aqueous dispersion of the attached functional group, like sulfonated carbon product, is treated with a salt like an alkyl ammonium salt. For instance, the alkylammonium salt can be a primary, secondary, tertiary, or quaternary ammonium salt. Treatment of the dispersed carbon product with the salt, e.g., ammonium salt, results in exchange of the sodium ion for the ammonium ion. When the alkyl group of the ammonium salt is large, flocculation of the carbon product occurs. The carbon product treated in this way is quite hydrophobic and floats to the surface of the water. This approach is attractive because the initial dispersion of carbon product allows each particle of carbon product to be well treated with hydrophobic groups. This preferred reaction is shown below, where R in this formula is at least one organic, monomeric, or polymeric group. The process described in U.S. Patent Application 08/663,694 filed June 14, 1996 can also be used and is hereby incorporated in its entirety by reference herein.



The amount of modified carbon product present in the polymeric product (where the polymeric product is not a masterbatch) can be amounts traditionally used with unmodified carbon products such as carbon black. For example, from about 0.01 wt% to about 50 wt%, more preferably from about 0.01 wt% to about 20 wt%, and most preferably, from about 0.01 wt% to about 5.0 wt% of the modified carbon product can be present based on the weight of the polymeric product.

The modified carbon products of the present invention can be used as masterbatches. In this embodiment, the modified carbon product is formed into a masterbatch just as conventional

masterbatches are formed. Accordingly, the modified carbon product can be added with standard masterbatch ingredients which may include waxes and polymers as well as other optional ingredients.

When the modified carbon products of the present invention are used to form masterbatches, generally, the amount of modified carbon product present can be amounts traditionally used with unmodified carbon products, such as carbon black, in masterbatches. However, with the modified carbon products of the present invention, masterbatches with higher loadings of carbon products are possible and thus masterbatches of the present invention can contain from about 10 wt% to about 95 wt% or more modified carbon product, and more preferably from about 50 wt% to about 90 wt% modified carbon product, based on the weight of the masterbatch.

The modified carbon products of the present invention can be incorporated or dispersed in the polymer to form the polymeric product using any means which permits the introduction of the reinforcement agents, fillers, or colorants like carbon black. Examples include hopper feeding of the modified carbon product into an extruder such as a single screw or multi-screw extruder, or an injection molder. Other means of introducing the modified carbon product into the polymer include mixers, like internal mixers, such as a Banbury and Brabender mixers. Other means of introducing, and preferably dispersing the modified carbon product in the polymer include, but are not limited to, long continuous mixers, continuous compounding extruders (e.g., Buss Kneader), tumble blenders, pelletizers and the like.

The polymeric products of the present invention, like any conventional polymer, can be formed and shaped into any desired article or shape.

Further, the polymeric products of the present invention include polymeric coatings and polymeric foams. With respect to polymeric coatings, typically an aqueous or non-aqueous solvent will be present in amounts typically found with respect to conventional polymeric coatings. With respect to polymeric foams, typically a foaming agent will be present in amounts conventionally found with respect to conventional polymeric foams.

The polymeric products of the present invention can include additional conventional ingredients typically found in polymers such as anti-oxidants, stabilizers (e.g., light/UV and thermal types), plasticizers, fillers, impact modifiers, lubricants, biocides, flame retardants, process

modifiers, antistatic agents, blowing (foaming) agents, colorants, antimicrobials, antiblocking agents, organic peroxides, optical brighteners, coupling agents, compatibilizers, process acids, mold release aids, tack additives, viscosity suppressants, reactive additives, fibers, antifogging agents, antihazing agents, bacteriocides, conductivity agents, cross-linking agents, delustering agents, dispersants, flexibilizers, flow control agents, fluorescent agents, fusion promoters, mildewcides and fungicides, nucleating agents, organic chelating agents, surface treatments, and the like, or other materials as described in Plastic Additives and Modifiers Handbook, Jesse Edenbaum, Ed., pp. 193-1086 (1992), incorporated herein by reference.

The present invention will be further clarified by the following examples, which are intended to be purely exemplary of the present invention.

In all of the examples, except when stated, a carbon black having a surface area of 90 m²/g (CTAB) and a DBPA of 98 cc/100g was used, in this case ELFT[®]EX TP from Cabot Corp.

Example 1

Carbon black (225 g) was slurried in 2 L of room temperature deionized water using an overhead mixer. Ethyl-4-aminobenzoate (4.5 g) was dissolved in 2.7 grams of 37% hydrochloric acid. Deionized water (100 mL) was added to dissolve the resulting salt. This solution was then added to the stirred carbon black slurry. Sodium nitrite (1.7 g) was dissolved in 50 mL of deionized water and then added to the stirred carbon black slurry. After several hours of mixing, the mixing was stopped. Upon standing, the mixture separated into three layers consisting of a top and bottom layer of carbon black separated by a colorless water layer. The mixture was filtered and the modified carbon black product was collected on a Bchner funnel using vacuum filtration. After washing the product with 2 L of deionized water, it was dried at 70°C to a constant weight.

Example 2

Fluffy carbon black (5kg) was treated at 70°C with sulfanilic acid (310 g) in a batch pin pelletizer. The pelletizer was charged with the carbon black and sulfanilic acid and the motor speed was set to about 200 rpm. The pelletizer was heated to 70°C. Sodium nitrite (125 g) was dissolved

in 1 L of water. The nitrite solution was added via a pressurized delivery system to the pelletizer. Likewise, 3 L of water were added. After all the water had been added, the batch was mixed for 3 minutes. Wet pellets of the sulfonated carbon black were then collected. The pellets were found to contain 42% water by weight. The wet pellets were used without drying for the ion exchange reactions below in Examples 2A-2D.

Example 2A

Wet sulfonated carbon black (387 g) was added with stirring to 2 L of room temperature deionized water. Cetyltrimethylammonium bromide (29.5 g) was dissolved in 500 mL of deionized water. The resulting solution was added to the stirred carbon black slurry. After several hours of mixing the stirring was stopped. The mixture slowly separated into three layers. The top layer consisted of black foam, the middle layer was clear while the bottom layer consisted of settled carbon black. The modified carbon product was collected on a Bchner funnel, washed with 2 L of deionized water and dried to a constant weight at 70°C.

Example 2B

Armeen SD (21.4 g from Akzo-Nobel) was added to 1.7 L of 10% acetic acid at room temperature. Once the amine was completely dissolved, 387 g of wet sulfonated carbon black was stirred in with an overhead mixer. Mixing was continued for 16 hours. As observed for the reaction with cetyltrimethylammonium bromide, the mixture separated into three layers. The modified carbon black product was collected on a Bchner funnel and washed with 2 L of a 50/50 mixture of ethanol and water followed by 2 L of water. The modified carbon black was dried to a constant weight at 70°C. This procedure was also followed using oleylamine and hexadecylamine.

Example 2C

To soyaalkyl amine (28.6 g, Adogen 172 D from Witco) was added to 6.49 g of acetic acid diluted with 150 mL of deionized water and 50 mL of ethanol. Once the amine was dissolved, it was added with stirring to 172 g of wet sulfonated carbon black dispersed in 2 L of room temperature

deionized water. After about 4 hours, the stirring was stopped and the mixture separated into three layers. The entire mixture was filtered using a Buchner funnel to isolate the modified carbon black product. It was then washed with 3 L of deionized water. The modified carbon black was dried overnight at 70°C to a constant weight.

5

Example 2D

A 1 L beaker was filled with 800 mL of deionized water and 50 g of carbon black. While stirring vigorously, the temperature was raised to 70°C. Sulfanilic acid (1.56 g) was added to the slurry. Next, a solution of sodium nitrite (0.62 g) in 3 mL of water was added to the stirred slurry.

10 The mixture was stirred overnight at 70°C. The resulting treated carbon black suspension was placed in a vacuum oven and dried at 70°C for several days to evaporate most of the water. The product contained about 40% water by weight.

The sulfonated carbon black thus prepared (50 g of wet carbon black) was mixed into 650 mL of room temperature deionized water in a 1L beaker. Mixing was accomplished using a magnetic
15 stirrer and a stir bar. Benzoic acid (0.66 g) and Amine D (1.51 g, from Hercules) were dissolved into 150 mL of toluene. Once both species were dissolved, the mixture was added directly to the dispersion of sulfonated carbon black. The resulting mixture was allowed to stir vigorously overnight. The modified carbon black product was isolated by evaporation of the water and toluene in a vacuum oven at 70°C. This method can also be employed using Foral 85 (also from Hercules)
20 instead of Amine D.

Example 3

Carbon black (200 g) was slurried in 2 L of room temperature deionized water using an overhead mixer. 4-aminobenzoic acid (4.94 g) was dissolved in 3.24 g of 70% nitric acid diluted
25 with 150 mL of deionized water. After 20 minutes of stirring, the 4-aminobenzoic acid was dissolved and the solution was added to the carbon black slurry. Sodium nitrite (2.42 g) was dissolved in 50 mL of deionized water. The resulting solution was added slowly to the carbon black slurry. Gas was evolved and the slurry became much less viscous. After 4 hours of mixing, the

overhead stirred was stopped. The modified carbon black product was isolated on a Buchner funnel, washed with 2 L of deionized water and dried to a constant weight at 70°C.

Next, the modified carbon black with attached carboxylic acid groups (50 g) was placed in a 1 L three necked round bottom flask. Toluene (200 mL) was added to the flask and the flask was fitted with a Dean-Stark trap. The trap was charged with toluene. To dry the modified carbon black of any residual water, the toluene-modified carbon black slurry was heated to reflux using a heating mantle. After 4 hours, 0.3 mL of water had collected in the trap. The slurry was cooled to room temperature under nitrogen. Uniline 425 from Petrolite Corp. (4.14 g), a long chain alkyl alcohol (C_{30} avg.), a p-toluenesulfonic acid (1.71 g) were added to the flask. A few drops of water had collected in the trap after heating the slurry at reflux for 3 hours. The slurry was cooled to room temperature under nitrogen.

The modified carbon black was collected on a Buchner funnel. An additional 300 mL of toluene was used to complete the transfer of the modified carbon black from the flask to the Buchner funnel. The modified carbon black was washed on the filter with 800 mL of a 50/50 ethanol and water mixture followed by 2 L of water. The modified carbon black was allowed to air dry for 4 hours before drying to a constant weight at 70°C.

Example 4

Control samples were prepared from carbon black pelletized in a laboratory scale batch pelletizer and from carbon black dried from slurry. The second treatment simulated the chemical treatment process, but used no reactive species. The carbon blacks were compounded at 2.5 wt% carbon black loading in high density polyethylene using a 1.6 liter Banbury internal mixer and four minute mixing cycle. Both data sets show the poor dispersion quality achieved with no chemical treatment. The results of compounding pelletized black in HDPE are shown in Table 1, and the results of compounding carbon black dried from slurry in HDPE are shown in Table 2. The overall average dispersion ratings were 1.78% undispersed area for pelletized black and 1.71% undispersed area for slurry dried carbon black.

Table 1: Direct Addition Controls, Process Pelletizer

Sample No.	Mean Undispersed Area %
1	1.42
2	1.56
3	1.90
4	1.94
5	2.04
6	2.26
7	1.54
8	1.60

Overall Average == 1.78

Sample 2 in Table 1 was a commercially available pelletized ELFTEx® carbon black product.

5 **Table 2: Direct Addition Controls, Carbon Black Dried from Slurry**

Sample No.	Mean Undispersed Area %
1	1.34
2	1.36
3	1.44
4	1.92
5	1.95
6	2.26

Overall Average == 1.71

Example 5

10 The modified carbon blacks from Examples 1-3 were compounded at 2.5 wt % carbon black loading in high density polyethylene (HDPE) using a 1.6 liter Banbury internal mixer and a four minute mixing cycle. The modified carbon black filled compounds were compared to compounds with unmodified carbon black compounded by the same method and to compounds prepared by first masterbatching the carbon black in HDPE at 40% loading, and then diluting the carbon black to 15 2.5% in a second processing step. The latter compounds represent the current state of the art for coloring plastics.

A Kontron plastics dispersion test was used to distinguish whether a chemical treatment improves the dispersion of carbon black in plastics. The Kontron plastics dispersion test measures the size and frequency of undispersed carbon agglomerates present in a calibrated, about 100 X,

digital micrograph of a thin polymeric film containing a low level (e.g., 2.5% by weight) of carbon black. The thin film was obtained by sandwiching small pieces of the carbon black pigmented polymer compound between glass slides and melting them, under heat and pressure. An automated image analysis program was used to identify and measure all carbon black agglomerates larger than 5
5 micron diameter. Undispersed area percent, the percent of the image that is covered by agglomerates, is the measured response used for ranking. An undispersed area percent of zero would be a perfect dispersion. The average undispersed area percent for ten images is reported.

The Kontron plastics dispersion test is based on ASTM D 2663, Method B, "Standard Test Methods for Carbon Black -- Dispersion in Rubber." Several modifications were made to the ASTM
10 test to allow measuring the dispersion of carbon black in plastics. The plastics films are about 10 times the thickness of rubber microtome sections, while the typical carbon black content in plastics is about 1/10th that of the typical carbon black content in rubber. As a result, the carbon black content as seen in a light micrograph is comparable for the two tests. In the ASTM test, carbon black agglomerates are identified and measured manually by inserting a calibrated grid into the microscope
15 optical path. An operator counts all grid squares that are at least half covered by an agglomerate. The sum of filled squares is converted to *Dispersion, %* by dividing the sum by the volume percent of carbon black in the compound. This process is automated in the Kontron plastics dispersion test.

Dispersion quality was improved using modified carbon products as shown in Tables 3-5. The modified carbon products were tested in the same manner as described above. Samples 1, 2, 4-
20 9, 11 and 12 of Table 3 were prepared as in Example 1 using the treatment and treatment level (mmol per gram of carbon black) described in Table 3. Samples 3 and 10 were prepared as follows:

Sodium nitrite (2.8 g) was added to 50 mL of concentrated sulfuric acid with stirring. Upon addition of the sodium nitrite, the solution turned orange. The temperature was raised to 70°C, then the solution was cooled. 4-Trifluoromethoxyaniline (7.2 g) or trifluoro methyl aniline at the
25 treatment level indicated in Table 3 was slowly added (over 15 minutes) at 30-35°C. The solution was stirred for two hours.

Carbon black (225 g) was slurried in 2 L of room temperature deionized water using an overhead mixer. The diazonium salt solution prepared above was then added to the slurry. Stirring

-25-

was continued for several hours. When stirring was stopped, the solution separated into three layers.

The top, middle, and bottom layers consisted of a small foamy layer of carbon black, a clear water layer and another carbon black layer. The bulk of the carbon black was contained in the bottom layer. The modified carbon black product was isolated by filtering the entire mixture through a

5 Bchner funnel. The modified carbon black product was washed on the filter with 2 L of water.

After washing, the modified carbon black was dried to a constant weight overnight at 70°C.

Table 3

Sample No.	Treatment	Treatment Level (mmol/g)	Mean Undispersed Area %
1	Ethyl-4-aminobenzoate	0.03	0.80
2	Ethyl-4-aminobenzoate	0.12	0.41
3	Trifluoro methyl aniline	0.36	0.62
4	dodecylaniline	0.12	0.96
5	dodecylaniline	0.18	0.74
6	dodecylaniline	0.18	0.80
7	dodecylaniline	0.36	0.89
8	4-tertbutyl aniline	0.18	0.75
9	4-tertbutyl aniline	0.36	0.77
10	Trifluoro methoxy aniline	0.18	0.79
11	4-ethyl aniline	0.12	0.88
12	4-ethyl aniline	0.36	0.96

10 The samples in Table 4 were prepared using the same procedure as recited in Example 2 for the primary treatment, and using the particular secondary treatment and secondary treatment level set forth in Table 4. The secondary treatment set forth in Table 4 was based on one of the procedures recited in Examples 2A, B, C, or D as indicated in Table 4.

The samples in Table 5 were prepared in the same manner as in Example 3 above.

Table 4

Sample No.	Primary Treatment	Secondary Treatment	Secondary Procedure (Example)	Treatment Mean Undispersed Area %	
1	Sulfonilic acid, sodium salt	Soya alkylamine	2B	0.36 & 0.36	0.21
2	Sulfonilic acid, sodium salt	Soya alkylamine	2B	0.36 & 0.36	0.74
3	Sulfonilic acid, sodium salt	Soya alkylamine	2B	0.36 & 0.36	0.76
4	Sulfonilic acid, sodium salt	Oleylamine	2B	0.36 & 0.36	0.25
5	Sulfonilic acid, sodium salt	Oleylamine	2B	0.36 & 0.36	0.82
6	Sulfonilic acid, sodium salt	Adogen 172D	2C	0.18 & 0.18	0.38
7	Sulfonilic acid, sodium salt	Foral 85	2D	0.18 & 0.18	0.42
8	Sulfonilic acid, sodium salt	CTAB	2A	0.18 & 0.18	0.46
9	Sulfonilic acid, sodium salt	Amine D	2D	0.36 & 0.36	0.69
10	Sulfonilic acid, sodium salt	Hexadecyl amine	2B	0.18 & 0.18	0.70
11	Sulfonilic acid, sodium salt	Di-tetradecyl glutamate p-toluene sulfonic acid	2B	0.36 & 0.36	0.69
12	Sulfonilic acid, sodium salt	Di-tetradecyl glutamate p-toluene sulfonic acid	2D	0.36 & 0.36	0.90
13	Sulfonilic acid, sodium salt	Amine D	2B	0.18 & 0.18	0.69
14	Sulfonilic acid, sodium salt	hexadecyl amine		0.36 & 0.36	0.70

5

Table 5

Sample No.	Primary Treatment	Secondary Treatment	Treatment Level (mmol/g)	Mean Undispersed Area %
1	4-aminobenzoic acid	Uniline425	0.18 & 0.18 mmol/g	0.75
2	4-aminobenzoic acid	Uniline700	0.18 & 0.18 mmol/g	0.85








Foral 85 and Amine D are terpene derivatives available from Hercules, Incorporated.






Adogen 172D is a soya alkylamine available from Witco. Uniline 425 and 700 are long chain






10 primary alcohols available from Petrolite, with average carbon lengths of C30 and C50, respectively.

As can be seen in the above Tables, the mean undispersed area was reduced using the modified carbon products of the present invention.

Examples of reactive groups which can be used in a process to make one or more types of the modified carbon product are set forth below in the Tables.

Name	Structure
ethyl-4-aminobenzoate	
4-dodecylaniline	
4-tert-butylaniline	
4-ethylaniline	
aniline	
4,4'-ethylenedianiline	
4-trifluoromethylaniline	

Name	Structure
4-trifluoromethoxyaniline	
sulfanilic acid	
4-aminobenzoic acid	
(4-aminophenyl)vinylsulfone	
4-aminophenyldisulfide	
sulfanilic acid and 4-dodecylaniline	
4-aminophenyldisulfide and 4,4'-ethylenedianiline	
ethyl-4-aminobenzoate and 4-aminobenzoic acid	

Name	Structure
hexadecylamine	
hexadecyltrimethylammonium bromide	
oleyl amine	
dimethyloleylamine	
soyaalkyl amines (Armeen® SD, Adogen® 715D)	mixture of oleyl amine, linoleylamine, linolenylamine
trimethyl soyaalkyl ammonium chlorides (Arquad S-50) $\text{AK}_{20}\text{N}_{6}\text{a1}$	mixture of quaternary ammonium salts of oleyl amine, linoleylamine, and linolenylamine
hydrogenated tallowamine	mixture of C18, C16, C14 n-alkyl primary amines
ditetradecylglutamate	
	Average carbon lengths
Uniline 350 (alkyl alcohol)	C26
Uniline 425 (alkyl alcohol)	C30
Uniline 550 (alkyl alcohol)	C40
Uniline 700 (alkyl alcohol)	C50

The modified carbon products of the present invention may provide for more economical preparation of polymer products (such as by reducing the number of processing steps or amount of processing needed), and/or may improve the characteristics of the polymer products. The improved dispersibility of the modified carbon products of the present invention may allow for improved dispersion in the polymer product, or make it possible to obtain a level of dispersion comparable to that achieved by existing compositions and processes using fewer steps or a reduced amount of processing. In terms of the characteristics of the polymer products, the modified carbon products of the present invention can improve characteristics such as hardness, rebound, impact resistance, colorfastness, abrasion resistance, and the like.

Other embodiments of the present invention will be apparent to those skilled in the art from consideration of the specification and practice of the invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with a true scope and spirit of the invention being indicated by the following claims.

WHAT IS CLAIMED IS:

1. A polymeric product comprising a polymer and a modified carbon product dispersed therein, wherein said modified carbon product comprises a carbon product having attached
5 at least one organic group having a C_{13} or higher alkyl group or polymeric group.
2. The polymeric product of claim 1, wherein said organic group further comprises an aromatic group or a second alkyl group.
- 10 3. The polymeric product of claim 1, wherein said organic group contains an ionic or an ionizable group.
4. The polymeric product of claim 1, wherein said organic group comprises a) at least one aromatic group and b) at least one ionic group, at least one ionizable group, or a mixture thereof,
15 wherein said aromatic group is directly attached to the carbon product.
5. The polymeric product of claim 1, wherein said organic group comprises a) a C_{13} - C_{100} alkyl group and b) at least one ionic group, at least one ionizable group, or a mixture thereof, wherein said C_{13} - C_{100} alkyl group is directly attached to the carbon product.
20
6. The polymeric product of claim 1, wherein said organic group is an olefin group, a styrenic group, an acrylate group, an amide group, an ester group, or mixtures thereof.
- 25 7. The polymeric product of claim 1, wherein said polymeric group is a polyolefin group, a polystyrenic group, a polyacrylate group, a polyamide group, a polyester group, or mixtures thereof.

-32-

8. The polymeric product of claim 1, wherein said organic group comprises:

-Ar-CO₂(C_mH_{2m+1}), where m = 0 to about 20;

-Ar-C(C_nH_{2n+1}), where n = 1 to about 50;

-Ar-C_pH_{2p}-Ar, where p = 1 to about 10;

5 -Ar-CX₃, where X is a halogen atom;

-Ar-O-CX₃, where X is a halogen atom;

-Ar-SO₃;

-Ar-SO₂(C_qH_{2q+1}), where q = 2 to about 10;

-Ar-S₂-Ar-NH₂;

10 -Ar-S₂-Ar-;

-Ar-SO₂-H;

or mixtures thereof.

9. The polymeric product of claim 1, wherein said organic group comprises:

15 -Ar-SO₃⁻ and -Ar(C_nH_{2n+1}), where n = 1 to about 50;

-Ar-S₂-Ar-NH₂ and -ArC_pH_{2p}-Ar, where p = 1 to about 10;

-Ar-S₂-Ar-;

-ArC_pH_{2p}-Ar, where p = 1 to about 10; or

at least two different -Ar-CO₂C_mH_{2m+1}, where m = 0 to about 20.

20

10. The polymeric product of claim 3, wherein said ionic or ionizable group comprises:

a carboxylic acid or salt thereof;

a sulfonic acid or salt thereof;

a quaternary ammonium salt;

25 a sulfonamide or a salt thereof;

SO₂NHCOR or a salt thereof, where R is a C₁-C₂₀ alkyl or a phenyl group or

mixtures thereof.

11. The polymeric product of claim 8, wherein said $-\text{Ar}-(\text{C}_6\text{H}_{2n+1})$ is a branched alkyl group.
12. The polymeric product of claim 8, wherein said $-\text{Ar}-(\text{C}_6\text{H}_{2n+1})$ is linear.
13. The polymeric product of claim 8, wherein $n = 4$ and $\text{C}_6\text{H}_{2n+1}$ is branched.
14. The polymeric product of claim 1, wherein said carbon product is carbon black, graphite, vitreous carbon, finely divided carbon, carbon fiber, activated charcoal, activated carbon, or mixtures thereof.
15. The polymeric product of claim 1, wherein said carbon product is carbon black.
16. The polymeric product of claim 1, wherein said polymeric product is in the form of a masterbatch.
17. A polymeric product comprising a polymer and a modified carbon product dispersed therein, wherein said modified carbon product comprises a carbon product having attached a group having the formula: $-\text{Ar}-\text{CO}_2-\text{R}$, or $\text{C}_6\text{H}_{2n}-\text{CO}_2-\text{R}$, where R is an organic group or a polymeric group.
18. The polymeric product of claim 17, wherein said R is an organic group.
19. The polymeric product of claim 17, where R is a polymeric group.
20. The polymeric product of claim 17, wherein said organic group is an alkyl group.
21. The polymeric product of claim 17, wherein said organic group is an aryl group.

22. The polymeric product of claim 17, wherein said organic group is an aralkyl group or alkylaryl group.

23. The polymeric product of claim 17, wherein said organic group is an olefin group, a styrenic group, an acrylate group, an amide group, an ester group, or mixtures thereof.

24. The polymeric product of claim 17, wherein said polymeric group is a polyolefin group, a polystyrenic group, a polyacrylate group, a polyamide group, a polyester group, or mixtures thereof.

10

25. The polymeric product of claim 17, wherein said organic group comprises a C_1 - C_{100} alkyl group.

26. The polymeric product of claim 17, wherein said organic group comprises a C_{20} - C_{∞} alkyl group.

15

27. The polymeric product of claim 17, wherein said polymeric product is a masterbatch.

20

28. The polymeric product of claim 17, wherein said carbon product is carbon black, graphite, vitreous carbon, finely divided carbon, carbon fiber, activated charcoal, activated carbon, or mixtures thereof.

25

29. The polymeric product of claim 17, wherein said carbon product is carbon black.

30. A modified carbon product comprising a) a carbon having attached at least one organic group directly attached to the carbon, b) at least one ionic group, ionizable group, or mixture thereof attached to said organic group, and c) at least one counter-ionic group with at least one

organic, monomeric, or polymeric group, counter-ionizable group with at least one organic, monomeric, or polymeric group, or a mixture thereof attached to said ionic group or ionizable group or both.

5 31. The modified carbon product of claim 30, wherein said monomeric group is a olefin group, a styrenic group, an acrylate group, an amide group, an ester group, or mixtures thereof.

 32. The modified carbon product of claim 30, wherein said polymeric group is a
10 polyolefin group, a polystyrenic group, a polyacrylate group, a polyamide group, a polyester group, or mixtures thereof.

 33. The modified carbon product of claim 30, wherein said organic group attached to
15 carbon product comprises a C_{13} - C_{100} alkyl group directly attached to the carbon product.

 34. The modified carbon product of claim 30, wherein said organic group attached to
said carbon product comprises an aromatic group attached directly to the carbon product.

 35. The modified carbon product of claim 30, wherein said organic group attached to
20 said carbon comprises an aralkyl group or an alkylaryl group directly attached to the carbon.

 36. The modified carbon product of claim 30, wherein said ionic group or ionizable
group is a carboxylic acid or salt thereof, a sulfonic acid or salt thereof, a quaternary ammonium salt,
a sulfonamide or salt thereof, SO_2NHCOR or a salt thereof, where R is a C_1 - C_{20} alkyl or an aryl
25 group.

 37. The modified carbon product of claim 30, wherein said counter-ionic group or
counter-ionizable group is a nitrogen based group or a phosphorous based group.

38. The modified carbon product of claim 30, wherein said ionic or ionizable group is a sulfonate group and said counter-ionic or counter-ionizable group is a nitrogen or phosphorous based group.

5 39. The modified carbon product of claim 30, wherein said organic group of the counter-ionic group or the counter-ionizable group is a C_1 - C_{30} alkyl group.

40. The modified carbon product of claim 30, wherein said organic group of the counter-ionic group or the counter-ionizable group is a C_1 - C_{20} alkyl group.

10

41. The modified carbon product of claim 30, wherein said organic group is a oleyl group.

42. The modified carbon product of claim 30, wherein said organic group is a oleyl group, a linoleyl group, a linolenyl group, or mixtures thereof.

15

43. The modified carbon product of claim 30, wherein said organic group is a 2-ditetradecylglutarate or hexa-decyl.

20 44. The modified carbon product of claim 30, wherein said carbon product is carbon black, graphite, vitreous carbon, finely divided carbon, carbon fiber, activated charcoal, activated carbon, or mixtures thereof.

45. The modified carbon product of claim 30, wherein said carbon product is carbon black.

25

46. A polymeric product comprising a polymer and the modified carbon product of claim 30 dispersed therein.

-37-

47. The polymeric product of claim 46, wherein said polymeric product is a masterbatch.

48. A polymeric product comprising a polymer and the modified carbon product of any one of claims 31 through 45.

49. A polymeric product comprising a polymer and the modified carbon product of claim 42.

50. A polymeric product comprising a polymer and the modified carbon product of claim 45.

51. The polymeric product of claim 50, wherein said polymeric product is a masterbatch.

52. The modified carbon product of claim 30, wherein said ionic or ionizable group is an anionic group and said counter-ionic or counter-ionizable group is a cationic group.

53. The modified carbon product of claim 30, wherein said ionic group or ionizable group is a cationic group and said counter-ionic or counter-ionizable group is an anionic group.

54. The modified carbon product of claim 30, wherein said counter-ionic group or counter-ionizable group is a carboxylic acid or salt thereof, a sulfonic acid or salt thereof, a quaternary ammonium salt, a sulfonamide or salt thereof, SO_2NHCOR or a salt thereof, where R is a $\text{C}_1\text{-C}_{20}$ alkyl or an aryl group.

55. The modified carbon product of claim 30, wherein said ionic or ionizable group is a nitrogen based group or a phosphorous based group.

56. A method for improving the dispersion of a carbon product in a polymeric product comprising dispersing a modified carbon product in a polymer, wherein said modified carbon product comprises a carbon product having attached at least one organic group or polymeric group which is compatible with said polymer.

5

57. A method for increasing the dispersion of a carbon product in a polymer product comprising dispersing a modified carbon product in a polymer, wherein said modified carbon product comprises a carbon product having attached a group having the formula $-\text{Ar}-\text{CO}_2-\text{R}$ or $-\text{C}_6\text{H}_4\text{CO}_2-\text{R}$, where R is an organic group or a polymeric group.

10

58. A method for increasing the dispersion of a carbon product in a polymeric product comprising dispersing the modified carbon product of claim 30 in said polymer, wherein said modified carbon product is compatible with said polymer.

15

59. The polymeric product of any one of claims 1 through 13 and 16 through 27 wherein said carbon product is an aggregate comprising a carbon phase and a silicon-containing species phase.

20

60. The polymeric product of any one of claims 1 through 13 and 16 through 27 wherein said carbon product is an aggregate comprising a carbon phase and a metal-containing species phase or said carbon product is a silica coated carbon black.

25

61. The modified carbon product of any one of claims 30 through 43 wherein said carbon product is an aggregate comprising a carbon phase and a silicon-containing species phase.

62. The modified carbon product of any one of claims 30 through 43 wherein said carbon product is an aggregate comprising a carbon phase and a metal-containing species phase or said carbon product is a silica coated carbon black.

63. A polymeric product comprising a polymer and the modified carbon product of claim 61.

5 64. A polymeric product comprising a polymer and the modified carbon product of claim 62.

INTERNATIONAL SEARCH REPORT

Inter. Appl. No.

PCT/US 98/26378

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08K9/04 C09C1/56

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C09C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 299 736 A (DATTA PABITRA) 10 November 1981 see claims 1,7	1
X	US 4 014 844 A (VIDAL ALAIN ET AL) 29 March 1977 see column 4, line 50 - line 56 see claim 1	1
X	GB 2 188 311 A (CABOT CORP) 30 September 1987 see claims 1,4	1
X	EP 0 289 231 A (ICI PLC) 2 November 1988 see claims 1-9	1
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

31 March 1999

Date of mailing of the international search report

13/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/26378

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 19134 A (CABOT CORP) 29 May 1997 see page 7 - page 8 see claims 1-24 ----	1-64
X	WO 96 18674 A (CABOT CORP) 20 June 1996 see claim 1 ----	8,9
X	US 5 630 868 A (ADAMS CURTIS F ET AL) 20 May 1997 see claim 1 -----	3-5

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/26378

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4299736	A	10-11-1981	DE 3119076 A	04-03-1982
			JP 57016045 A	27-01-1982
US 4014844	A	29-03-1977	FR 2094590 A	04-02-1972
			DE 2130617 A	30-12-1971
			GB 1348850 A	27-03-1974
GB 2188311	A	30-09-1987	AU 599087 B	12-07-1990
			AU 7050287 A	01-10-1987
			BE 906089 A	16-04-1987
			BR 8701003 A	29-12-1987
			CN 1025863 B	07-09-1994
			CZ 8701869 A	17-04-1996
			DD 258996 A	10-08-1988
			DE 3703077 A	01-10-1987
			DK 147287 A	25-09-1987
			FR 2596055 A	25-09-1987
			IN 168779 A	01-06-1991
			JP 1025785 B	19-05-1989
			JP 1541228 C	31-01-1990
			JP 62275164 A	30-11-1987
			KR 9506688 B	21-06-1995
			LU 86811 A	12-08-1987
			MX 168266 B	14-05-1993
			NL 8700664 A	16-10-1987
			PT 84488 B	10-11-1989
			SE 465464 B	16-09-1991
			SE 8700311 A	25-09-1987
EP 0289231	A	02-11-1988	AU 600819 B	23-08-1990
			AU 1533588 A	03-11-1988
			JP 63284265 A	21-11-1988
			US 5071891 A	10-12-1991
WO 9719134	A	29-05-1997	US 5747559 A	05-05-1998
			AU 1120597 A	11-06-1997
			CA 2238265 A	29-05-1997
			EP 0862597 A	09-09-1998
			NO 982300 A	21-07-1998
WO 9618674	A	20-06-1996	US 5559169 A	24-09-1996
			AU 693983 B	09-07-1998
			AU 4353396 A	03-07-1996
			CA 2207544 A	20-06-1996
			EP 0797619 A	01-10-1997
			JP 10510574 T	13-10-1998
			ZA 9510663 A	16-07-1996
US 5630868	A	20-05-1997	US 5571311 A	05-11-1996
			US 5554739 A	10-09-1996
			AU 4378596 A	03-07-1996
			BR 9509137 A	21-07-1998
			CN 1160415 A	24-09-1997
			EP 0797636 A	01-10-1997
			HU 77797 A	28-08-1998
			JP 10510862 T	20-10-1998
			WO 9618695 A	20-06-1996
			ZA 9510667 A	29-05-1996

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/26378

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5630868 A		AU 692349 B	04-06-1998
		AU 4471996 A	03-07-1996
		AU 4472096 A	03-07-1996
		AU 4472196 A	03-07-1996
		BR 9510016 A	28-10-1997
		BR 9510057 A	16-06-1998
		BR 9510058 A	16-06-1998
		CA 2207427 A	20-06-1996
		CA 2207455 A	20-06-1996
		CA 2207475 A	20-06-1996
		CN 1175272 A	04-03-1998
		CN 1175268 A	04-03-1998
		CN 1175271 A	04-03-1998
		CZ 9701841 A	12-11-1997
		CZ 9701843 A	15-07-1998
		CZ 9701844 A	15-07-1998
		EP 0799282 A	08-10-1997
		EP 0797637 A	01-10-1997
		EP 0797635 A	01-10-1997
		HU 77809 A	28-08-1998
		HU 77808 A	28-08-1998
		JP 10510797 T	20-10-1998
		JP 10510863 T	20-10-1998
		JP 10510864 T	20-10-1998
		NO 972734 A	11-08-1997
		NO 972735 A	13-08-1997
		NO 972737 A	08-08-1997
		PL 320729 A	27-10-1997
		PL 320731 A	27-10-1997
		PL 320736 A	27-10-1997
		SI 9520128 A	30-04-1998
		SI 9520129 A	30-04-1998
		SI 9520130 A	30-04-1998
		WO 9618690 A	20-06-1996
		WO 9618696 A	20-06-1996
		WO 9618694 A	20-06-1996
		US 5713988 A	03-02-1998